

Clear Coat Blending:

BASF recommends applying the specified amount of clear to the <u>entire</u> panel when doing Basecoat/Clearcoat repairs. This will make the repair eligible for the Glasurit or R-M lifetime warranty.

Because there are situations when clearcoating an entire panel is not desirable, when a roof and a quarter panel have no break-off point for example, BASF has developed processes and products for blending clearcoats. These processes and products can be found in the Glasurit and R-M technical manuals.

Blending the clearcoat requires that the thickness of clear be reduced in the blend area. This can result in the clearcoat blend edge becoming visible after a period of exposure to the weather. The blend edge can also become visible if it is polished too aggressively.

For these reasons, BASF will <u>not</u> warrant the blended edges of clearcoats. Blending procedures recommended by BASF are intended to be used only as a cost saving measure in those instances that an economical repair is required.

J Skurka Rev. 3/20/00 Clear Coat Blending.doc